

## ACCELERATED ELECTROCHEMICAL METHOD FOR STUDYING THE CORROSION BEHAVIOR OF AISI321 STAINLESS STEEL FOOD GRADE IN ACIDIC FOOD ENVIRONMENTS

Silviu-Gabriel STROE<sup>1</sup>

e-mail: silvius@fia.usv.ro

### Abstract

The purpose of this research was to study by electrochemical methods the behavior of AISI321 stainless steel food grade samples in acidic corrosive environments. 3%, 6% and 9% CH<sub>3</sub>COOH solutions in bidistilled water were used. The volume of solution studied was 300 ml. The exposure time of the stainless steel samples was 90 min. and the exposure temperature was 22±1°C. In order to achieve the proposed objective was been used a complex system consisting of a potentiostat-galvanostat Wenking (HP 96-20), two multimeters Hameg (HM 8112-3) for voltage monitoring, an original electrochemical cell and a computer for programming, acquisition and interpretation of experimental data. In order to develop the mass balance the theoretical masses of <sup>56</sup>Fe, Mn, Cr, Ni and Ti metal ions which migrated in corrosive solutions were calculated. The chemical analysis of corrosive solutions after migration tests was performed by ICP-MS method. The dissolution rates of metal ions studied were calculated. The results obtained demonstrate the validity of the accelerated electrochemical method in laboratory tests for the study of the migration phenomena of metal ions in acidic food environments.

**Key words:** stainless steel, electrochemical cell, migration, mass balance, dissolution rate

Austenitic stainless steels are widely used in food raw material processing industry because have a good corrosion resistance in a very wide range of food environments (Ait Albrimi Y., 2011) (Alves H., Agarwal D. C., 2006). One of the most popular austenitic stainless alloys are chromium-nickel-iron alloys also known as the 300 series. The AISI321 stainless steel grade has a very good corrosion behavior in a wide variety of corrosive environments, including food products, the sterilizing solutions and organic and inorganic chemicals (Page G. G., 1987). In literature there are indications of corrosion behavior of the steel grades, but most often in pure acid solutions, the results being taken only as a guide for behavior in these environments.

Electrochemical techniques are very efficient and inexpensive tool for all investigations laboratory for studying the corrosion mechanisms. In addition to their application in basic research, electrochemical techniques are of great application in the monitoring of any change in ionic balance or migration of electrons occurring on the surface of the electrode or at the interface between the metal and the environment (Bard A., Faulkner L., 2001), (Gulaboski R., Pereira C.M., 2008). More than that, electrochemical techniques have proven also

very useful tools to study the phenomena of adsorption to the electrode surface (Bagotsky V.S., 2005). Among the electrochemical techniques used in this field are voltammetry and potentiometry. Their widespread application is due to very good sensitivity for a very wide range of concentrations of organic and inorganic compounds, short time analysis, providing a precise relationship between the measured signal (current intensity) and concentration, all at an average cost of processing equipment.

A large number of researches are shown in the scientific literature that various methods have been applied to the study of electrochemical phenomena in food systems interface (Wever D.J., Veldhuizen A.G., 1998), (Jafarian M., Gobalb F., 2008), (Pardo A., Merino M.C., 2008), (Ningshen S., Mudali U.K., 2009), (Stoica M., Bahrim G., 2012).

In addition, a large number of analyzes performed to determine the electrochemical behavior of metal alloys in contact with the food used in parallel some spectrometric techniques. Thus, lately have been developed and implemented many electrochemical techniques for studying behavior under specific metals and alloys in the food industry (Zou Y., Wanga J., 2011).

<sup>1</sup> Faculty of Food Engineering, Stefan cel Mare University of Suceava, Suceava, Romania

## MATERIAL AND METHOD

The aim of this research was to study by electrochemical methods the behavior of AISI321 stainless steel food grade samples in acidic corrosive environments. This paper is a continuation of the researches carried out on samples from 300 stainless steel series (Stroe S. G., 2013). The aim was to increase the dissolution rate with direct effect on the limit of detection of heavy metal ions from solutions, the accuracy of measurement of the concentration of metal ions as well as productivity growth of the analytical research by reducing the time required for corrosion and diffusion.

For studying the corrosion behavior of metal discs samples were used with a diameter of 40 mm and a thickness of 2.5 mm. The sampling and sample preparation used in the experiment was made as described in the EFSA guidance note (EFSA, 2008). In order to avoid the contamination of the corrosive environment with foreign compounds from the surfaces of the samples materials (for removal of oil), which had been washed with a detergent solution at  $40\pm 1^\circ\text{C}$ , rinsed with double distilled water at  $40\pm 1^\circ\text{C}$  and then placed in the ultrasonic bath Elma H-78224 for 15 minutes. The samples were then dried in the oven at a temperature of  $40\pm 2^\circ\text{C}$ . In order to determine the surface roughness a  $\mu\text{Scan}$  system, manufactured by *NanoFocus*, was used. The measurement and the calculation of the commonly parameters of surfaces was carried out according to *DIN EN ISO 4287* and *DIN EN ISO 4288*. The average value of the surfaces roughness has been  $R_a=0.783125\ \mu\text{m}$ . To determine the chemical composition of the AISI321 stainless steel samples the LA-ICP-MS method was used. For this purpose a laser ablation

system was used - model UP213 (New Wave Research), coupled with mass spectrometer with inductively coupled plasma, ICP-MS - model 7500 (Agilent Technologies). The concentrations of the alloying and micro-alloyed elements of the stainless steel samples are consistent with the concentrations provided by SR EN 10088-2:2005.

The chemical composition of the stainless steel is shown in *table 1*.

Table 1

**Chemical composition of the AISI321 stainless steel samples [wt %]**

Fe	C	Mn	P	S	Si	Cr	Ni	Ti
68	0.08	2.0	0.045	0.03	0.75	18	11	0.4

Acetic acid solutions of 3%, 6% and 9%  $\text{CH}_3\text{COOH}$  in bidistilled water were used in the experimental research. The solution temperature was maintained at  $22\pm 1^\circ\text{C}$  using a thermostatic bath Therm Phoenix II. The exposure time of samples for carrying out the electrochemical accelerated test was 90 min.

In order to conduct the accelerated electrochemical tests a conventional system was used; the system consisted in a potentiostat-galvanostat Wenking HP 96-20 (Bank Elektronik, Germany), two multimeters Hameg HM8112-3 (Hameg, Germany) to monitor the voltage values, an original electrochemical cell and a PC system for programming, acquisition and interpretation of experimental data obtained. AISI321 stainless steel discs were used as a both working and counter electrode. The stainless steel discs were used as working and counter electrode by mounting them in supports made of polytetrafluoroethylene (teflon) (*figure 1 a, b*).




Figure 1 a The principle scheme of potentiostat-galvanostat system for studying the corrosion behavior of AISI321 stainless steel: 1 - potențiostat-galvanostat Wenking HP 96-20; 2 - electrochemical cell; 3 - Hameg HM8112-3 multimeter for working voltage monitoring; 4 - Hameg HM8112-3 multimeter for recording the current intensity values in the electrochemical cell; 5 - PC system; 6 - thermostatic bath

Figure 1 b Spatial view of the electrochemical cell: 2a - working electrode; 2b - counter electrode

The electrochemical cell voltages measured by the HM 8112-3 Hameg multimeter are shown in *table 2*.

The metal species studied were  $^{56}\text{Fe}$ ,  $\text{Mn}$ ,  $\text{Cr}$ ,  $\text{Ni}$  and  $\text{Ti}$ .

In order to develop the mass balance of the metal species migrated from AISI321 stainless steel samples in corrosive solutions the theoretically and the real balance were calculated.

Table 2  
Voltage in electrochemical cells

Concentration solution, [%]	3	6	9
Voltage, [V]	6.5	6.5	7.0

To determine the theoretical masses of the metal species dissolved in acetic acid solutions the Faraday's law was applied (law of electrolysis), which stipulates that the mass dissolved is proportional to the amount of electricity that runs through the system. Therefore, the amount of metal dissolved from the anode is equal to the product of the gram equivalent of the metal species studied, the electric current intensity and the electrolysis time (relation 1):

$$m = k \cdot I \cdot t \quad (1)$$

where,

$m$  - amount of metal dissolved from the anode, [g];

$k$  - gram equivalent of the species;

$I$  - the current intensity in the electrochemical cell, [A];

$t$  - time of electrolysis, [min.].

The value of  $k$  was calculated using the equation:

$$k = \frac{A}{z \cdot F} \quad (2)$$

where,

$A$  - atomic mass of species, [g];

$z$  - valence of the species (Fe, Mn, Cr, Ni, Ti);

$F$  - Faraday's constant ( $F=9.648533 \times 10^4 \text{ C} \cdot \text{mol}^{-1}$ )

$$A_p = \frac{A_{Ni} \cdot \%Ni + A_{Cr} \cdot \%Cr + A_{Fe} \cdot \%Fe + A_{Mn} \cdot \%Mn + A_{Ti} \cdot \%Ti}{5} \quad (5)$$

## RESULTS AND DISCUSSION

In table 3 presents the values of the electrolysis current in potentiostatic regime, according to the time, at various concentrations of acid food simulant environment, based on the relationship between electrolytic current and the mass of the anode metal dissolved in the electrochemical cell.

Table 3  
The electric current values for the AISI321 stainless steel samples in 3%, 6% and 9% CH<sub>3</sub>COOH solutions

Exposure time, [min.]	Current value, [A]		
	3%	6%	9%
90	0.1290	0.1710	0.1972

The values of  $m$  calculated using the Relation 1 were used to develop the theoretical mass balance. For developing of the real mass balances the acid solutions were analyzed by ICP-MS method.

In order to study the corrosion phenomenon that occurs in the electrochemical cell the dissolution rate,  $\eta$ , was calculated (relation 3):

$$\eta = \frac{m_p}{m_t} \quad (3)$$

where,

$m_p$  - practical masses calculated from the concentration of metal species obtained by the ICP-MS analysis, [g];

$m_t$  - theoretical masses obtained used the Relation 1, [g];

The concentrations of electrolysis baths after 90 min. were calculated using the relation 4:

$$C = \frac{m}{V} \rightarrow m_p = C \cdot V \quad (4)$$

where,

$C$  - concentration of the species analyzed by ICP-MS method, [ppb];

$m_p$  - practical mass, [g];

$V$  - solution volume - 300, [ml].

Relation 1 was used to calculate the theoretical mass of dissolved metal ions, using the weighted atomic mass ( $A_p$ ), based on the ion concentration in the stainless steel samples (relation 5):

The values reflect the kinetics of anodic dissolution of metal ions from the AISI321 stainless steel samples.

Table 4 presents the theoretically weight values to be dissolved [g] for metal ions from the samples of AISI321stainless steel grade after 90 min.

The values of dissolved real masses [g] of the metal ions studied and found in the simulant acid solutions (CH<sub>3</sub>COOH), obtained with the ICP-MS spectrometer, are shown in table 5. Thus, the dissolution rates  $\eta$  were calculated, using the relation 3.

The values of the dissolution rates  $\eta$  [%] of the dissolved metal ions from AISI321 stainless steel samples in acid simulant solutions are shown in table 6.

Table 4  
The theoretical masses as possible to be dissolved (if the dissolution rate should be 100%) for the metal ions from AISI321 stainless steel samples after 90 min., [g]

Chem elem.	Ni	Cr	<sup>56</sup> Fe	Mn	Ti
Conc. [wt%]					
3	0.03900	0.02600	0.03900	0.03900	0.01900
6	0.05200	0.03500	0.05200	0.05200	0.02600
9	0.06000	0.04000	0.06000	0.06000	0.03000

Table 5

**The real masses dissolved in acid simulant solutions from AISI321 stainless steel samples after 90 min., [g]**

Chem elem. Conc. [wt%]	Ni	Cr	<sup>56</sup> Fe	Mn	Ti
3	0.00016	0.01414	0.00011	0.00106	0.00019
6	0.00017	0.01579	0.00014	0.00136	0.00023
9	0.00056	0.01691	0.00015	0.00159	0.00026

Table 6

**The dissolution rates  $\eta$  of the metal ions in the 3%, 6% and 9% CH<sub>3</sub>COOH simulant solutions, [%]**

Chem elem. Conc. [wt%]	Ni	Cr	<sup>56</sup> Fe	Mn	Ti
3	0.00424	0.53430	0.00292	0.02687	0.01002
6	0.00323	0.45011	0.00264	0.02590	0.00866
9	0.00938	0.41787	0.00263	0.02623	0.00847

By studying the values shown in *table 6* one can see that the lowest dissolution rates were obtained for iron and the highest dissolution rates were obtained for the chromium. Generally, it can be said that the dissolution rate of metal ions in acid simulant solutions decreases with increasing the concentration of CH<sub>3</sub>COOH.

### CONCLUSIONS

The experimental researches that have been carried out on AISI321 stainless steel samples, under accelerated corrosion regime, using an electrical gradient overlapped a concentration gradient, as well as results obtained, have validated the validity of the method used. The dissolution rate of the metal ions in the electrochemical working regime with electrical current gradient substantially increases compared to of using the concentration gradient only. Using the potentiostatic electrochemical technique allows the variation from almost nearly of corrosion speed and thereby also establish the optimal working conditions without achieve simulant solutions with different concentrations.

### ACKNOWLEDGMENTS

I would like to thank Prof. G. Gutt from the Faculty of Food Engineering Suceava, for the permanent scientific guidance and logistical support for this research. Without his constant guidance and help this paper would not have been possible.

### REFERENCES

- Ait Albrimi Y., Eddib A., Douch J., Berghoute Y., Hamdani M., Souto R.M., 2011** - *Electrochemical Behaviour of AISI 316 Austenitic Stainless Steel in Acidic Media Containing Chloride Ions*, International Journal of Electrochemical Science, 6, p. 4614 - 4627.
- Alves H., Agarwal D.C., Werner H., 2006** - *NACE - International Corrosion Conference Series*, Houston, USA.
- Bagotsky V.S., 2005** - *Fundamentals of Electrochemistry*, 2nd ed., Wiley, New York.
- Bard A.J., Faulkner L., 2001** - *Electrochemical Methods*, ISBN: 978-0-471-04372-0, Wiley, New York.
- Gulaboski R., Pereira C.M., 2008** - *Electroanalytical Techniques and Instrumentation in Food Analysis, Otlis/Handbook of Food Analysis Instruments*, 45660\_C017, p. 379.
- Jafarian M., Gobalb F., Danaeea I., Biabania R., Mahjania M.G., 2008** - *Electrochemical studies of the pitting corrosion of tin in citric acid solution containing Cl*, Electrochimica Acta, Volume 53, Issue 13, p. 4528–4536.
- Ningshen S., Mudali U.K., Amarendra G., Raj B., 2009** - *Corrosion assessment of nitric acid grade austenitic stainless steels*, Corrosion Science 51, p. 322–329.
- Page G.G., 1984** - *Corrosion Failures of 304/316 Stainless Steels in the Food Industry*, Food Technology in New Zealand.
- Pardo A., Merino M.C., Coy A.E., Arrabal R., Viejo F., Matykina E., 2008** - *Corrosion behaviour of magnesium/aluminium alloys in 3.5 wt.% NaCl*, Corrosion Science 50, p. 823–834.
- Stoica M., Bahrim G., Dinica R., Cârăc G., 2012** - *Electrochemical study of stainless steel characteristic modification on correlative effect of fungal cell suspension and ActiSEPT used as biocide for equipment disinfection in bioprocessing of food*, Journal of Optoelectronics and Advanced Materials, Vol. 14, No. 3-4, p. 317 - 322.
- Stroe S.G., 2013** - *Study of corrosion behavior of AISI304 stainless steel samples using accelerated electrochemical methods*, Journal of Faculty of Food Engineering, Stefan cel Mare University of Suceava, Romania, Volume XII, Issue 4 – 2013, p. 354 - 358.
- Wever D.J., Veldhuizen A.G., de Vries J., Busscher H.J., Uges D.R.A., van Horn J.R., 1998** - *Electrochemical and surface characterization of a nickel–titanium alloy*, Biomaterials, 19, p. 761–769.
- Zou Y., Wanga J., Zheng Y.Y., 2011** - *Electrochemical techniques for determining corrosion rate of rusted steel in seawater*, Corrosion Science 53, p. 208–216.
- \*\*\* - **EFSA 2008** - *EFSA. Food Contact Materials, Note for Guidance*, Updated on 30/07/2008.